

Nyalic Data Sheet

Pot life		Indefinite in closed container
Solids		
	By Weight	27.31%
	By Volume	23.66%
V.O.C		674 gms / litre
Dry Time		ASTM D-1640 & Gardner Dry Time Recorder
	3mils @25C	
	To Touch	10 - 12 minutes
	Tack Free	15 - 16 minutes
	Hard	20 - 22 minutes
Flash Point		ASTM D - 56-closed cup 63.8 degrees C
Coverage		Approximately 33 square meters per litre at WFT yields 12 - 15 microns DFT
Material Temperature		Between 18 - 35C, ideal temperature 25C
Surface Temperature		Between 10 - 49C
Ambient Temperature		Between 13 - 49C with relative humidity not exceeding 85%. Do not apply if temperature is less than 5% above dew point.
Flexibility		Mandrel bend test 3mils passed